

Date: 14.09.2017

Test Certificate n° 1653

Applicant: Lapitec S.p.A.
Via Bassanese, 6
31050 Veduggio (Italia)

Date of request: 06.07.2017

Date of sample receipt: 06.07.2017

Type of sample: Sintered stone slab 3400x1500x20 mm

Type of test required: Determination of flexural strength according to EN-14617-2

Date of test execution: 04.09.2017

Number, shape and size of the specimens in the sample 4 slabs 3400x1500x20mm
4 samples sizing 150x60x20 mm have been cut from each slab

Results: Flexural strength average value: 52.96 Mpa


Slab n.1	Slab n.2	Slab n.3	Slab n.4
52.64	52.27	52.32	53.36
52.47	52.99	52.81	54.01
54.46	52.21	52.11	52.46
53.77	53.60	53.22	52.78

Deviations from the standard and their justification:

Remarks:


Analyst

Tonellato Cesare



R&D Manager

Zeggio Stefano



The results contained in this Test Certificate refer exclusively to the samples tested.
Moreover, Breton R&D Dept. does not take any responsibility as for the origin of the materials tested.
This Certificate must be reproduced in full, unless authorization of Breton R&D Dept.